

GEOLOGICAL SURVEY CIRCULAR 234



SPECTROGRAPHIC IDENTIFICATION
OF MINERAL GRAINS

By J. N. Stich

GEOLOGICAL SURVEY CIRCULAR 234



SPECTROGRAPHIC IDENTIFICATION
 OF MINERAL GRAINS

By J. N. Stinch

UNITED STATES DEPARTMENT OF THE INTERIOR
Oscar L. Chapman, Secretary

GEOLOGICAL SURVEY
W. E. Wrather, Director

GEOLOGICAL SURVEY CIRCULAR 234

SPECTROGRAPHIC IDENTIFICATION OF MINERAL GRAINS

By J. N. Stich

This report concerns work done on behalf of the
U. S. Atomic Energy Commission
and is published with the permission of the Commission

Washington, D. C., 1953

Free on application to the Geological Survey, Washington 25, D. C.

SPECTROGRAPHIC IDENTIFICATION OF MINERAL GRAINS

CONTENTS

	Page	Page
Abstract.....	1	Results and tables..... 5
Introduction.....	1	Future program..... 5
Discussion.....	2	Literature cited..... 5
Methods.....	2	Composition of standard
Procedure.....	3	solutions..... 14

TABLES

	Page
Table 1. Sensitivities on the basis of 1-mg samples for the elements determined by the microqualitative method.....	7
2. Wavelengths and sensitivities of the analytical lines used in the microqualitative method.....	7
3. Comparison of chemical quantitative and spectrographic qualitative microanalyses of samples of uranium minerals.....	11
4. Mineral identifications accomplished by agreement of spectrographic microqualitative analyses with data from X-ray diffraction patterns.....	12

ABSTRACT

A qualitative spectrographic method of analysis of single mineral grains, impurity inclusions, X-ray powder spindles, and other small samples weighing 1 mg or less is described. Samples weighing as little as 0.01 mg have been analyzed. Where 1 mg of sample is available, the accuracy of the method approaches that of a semiquantitative method. During a 10-month period, 20,000 determinations of 69 metallic and metalloid elements in more than 300 small samples have been made with the method. In conjunction with petrographic, physical, and X-ray methods, these determinations of chemical composition have been useful in establishing the mineral identity of small single grains. A direct-current arc is used. The use of a standardization solution that includes only one element per plate greatly facilitates the selection of reliable analytical lines. A small carbon electrode cut from graphite stock 1/8-in. in diameter is used; this is convenient for the loading and arcing of X-ray powder spindles. The medium-size quartz-prism spectrograph is preferable to a grating instrument for qualitative microanalysis as its complete spectrum coverage for a single exposure includes the most sensitive lines of the alkali elements.

INTRODUCTION

In connection with the investigation of radioactive raw materials conducted by the U. S. Geological Survey on behalf of the Atomic Energy Commission, a large number and variety of samples are received for spectrographic analysis.

Among these samples are many that are available only in 1-mg amounts or less and consist chiefly of mineral grains and impurity inclusions hand-picked under a petrographic microscope from many rocks and ores being studied. Because these small samples are composed of grains selected individually and may occasionally include but one grain each, they are also referred to as "single-grain" samples.

Although many of these grains can be identified on the basis of such properties as crystal structure, index of refraction, hardness, specific gravity, and X-ray diffraction pattern, frequently their chemical composition must also be determined in order to establish their mineral identity (Lee and Wright, 1939).

Owing to the small size of the samples, which generally limits the duration in the arc of their characteristic spectra to a few seconds or less, the application of a visual spectroscope (Peterson and others, 1947; Jaffe, 1949) is restricted to the determination of one or two major elements at a time. Also, unless larger samples are used, many elements, such as arsenic, boron, and phosphorus, whose principal emission lines occur in the ultraviolet range not visible to the eye, cannot be detected with the spectroscope.

The use of the more sensitive spectrograph, however, permits the rapid qualitative analysis of single-grain samples for a complete range of metallic and metalloid elements in concentrations down to 0.1 percent and lower. Another advantage of the spectrograph is that, in the form of a spectrogram

recorded on a photographic plate, it produces an objective and permanent record of the analysis of a sample.

The author is indebted to his associates of the Geological Survey for their help and cooperation, particularly to A. W. Helz for his invaluable technical aid and to C. L. Waring whose suggestions contributed materially to the scope of this paper. Special thanks are due also to C. S. Annell for the use of his standard solutions, to Alice Dowse Weeks and Mary E. Thompson for providing many of the samples, to Evelyn Cisney and Joseph Berman for the X-ray diffraction pattern checks, and to A. M. Sherwood for most of the chemical microanalyses.

DISCUSSION

In addition to inclusions and small single grains, the types of samples analyzed included magnetic separates, fragments of mineralized wood, placer sand, sediments, chemical precipitates, distilled water residues, furnace slags, and corrosion products. Samples weighing as little as 0.01 mg were analyzed. During a period of ten months, 20,000 determinations of 69 metallic and metalloïd elements (table 1) in more than 300 small samples were analyzed by the method.

The single-grain samples are received in the form either of the grains themselves or more often of

ethyl cellulose X-ray powder spindles containing the grains.

The practice of arcing X-ray spindles rather than duplicate samples of the grains is advantageous because it reduces the amount of separation work required and also permits the data from the spectrograms of the arced spindles to be checked directly with that from the X-ray diffraction patterns previously obtained.

The spectrographic results are reported qualitatively as "major," "minor," and "trace," corresponding approximately to brackets of 10 percent and over, 1-10 percent, and 0.1-1 percent concentrations. With single-grain samples and X-ray spindles these results are used specifically (1) to confirm the chemical compositions of minerals tentatively identified by their X-ray diffraction patterns and other properties, (2) to determine impurities in the minerals, and (3) to differentiate between minerals producing similar X-ray diffraction patterns, such as metatorbernite and metazeunerite. If no patterns are obtained, the spectrographic reports aid further study and purification work.

Some of the minerals that have been analyzed and whose identifications have been confirmed by checks of the spectrographic results with the X-ray diffraction patterns are:

Uranium-bearing and rare-earth minerals

Allanite	Cyrtolite	Rauvite	Torbernite
Autunite	Euxenite	Saléeite	Tyuyamunite
Bastnaesite	Florencite	Samaraskite	Uraninite
Beta-uranotil	Huttonite	Skłodowskite	Uranocircite
Brannerite	Kasolite	Soddyite	Uranophane
Carnotite	Parisite	Thorite	Zeunerite
Cuprosklodowskite	Phosphuranylite		

Miscellaneous minerals

Apatite	Franklinite	Magnetite	Rutile
Apophyllite	Gibbsite	Melanovanadite	Smaltite-cloanthite
Azurite	Goethite	Montroseite	Soda-niter
Barite	Halite	Orpiment	Sphalerite
Biotite	Hematite	Pyrrargyrite	Talc
Calcite	Hewettite	Pyrochlore-microlite	Topaz
Cerussite	Hydromica	Quartz	Vosenite
Chrysocolla	Ilmenite	Realgar	Zircon
Conichalcite	Kaolinite		

METHODS

The spectrographic method of microanalysis initially applied to this wide variety of minerals utilized a 220 d-c volt arc at 10 amp and an Eagle-mounted 3-meter grating spectrograph. The d-c arc was chosen because, generally, it gives the highest sensitivity (Nachtrieb, 1950). As the method involved a determination of major and minor elements in very small samples, the use of the same excitation conditions favorable to the determination of trace elements in larger samples was indicated.

The standards used consisted of four mixtures containing 10 different elements each, prepared in

1, 0.1, and 0.01 percent series of concentration, with silica as the base material. Because the use of 1 mg amounts of each of the standard mixtures in the preparation of the standard plates was based on taking 1 mg of the unknown sample, 10 percent standard spectrograms were obtained by using 10-mg amounts of the 1 percent mixtures. The arrangement of the elements within each mixture followed that described by Van Tongeren (1938).

This procedure had two serious limitations: (1) as the exposures were made in the generally useful range of 2450-3850 Å, the single-exposure spectrum coverage of only 1400 Å did not include the most sensitive lines of the alkali elements; and

(2) the complexity of the spectrograms of the 1 percent standard mixtures, that made it difficult to select and identify the reliable analytical lines for each element.

The disadvantage of limited wavelength coverage for a single exposure applied also to the Wadsworth-mounted 21-ft grating spectrograph. With its grating set to cover the ultraviolet range down to 2250 Å, the upper wavelength limit effective is at 4750 Å, which falls short of the 5890-7700 Å region where the persistent K, Li, and Na lines are located. The detection limits of K and Na with the grating spectrographs set in the ultraviolet range are only about 10 percent on the basis of 1 mg of sample.

When a medium quartz prism spectrograph accommodating 14-in. plates and permitting a single-exposure coverage of the entire range from 2080 to 10,000 Å became available, the method was transferred to this instrument. The d-c arc was retained. At the same time the solution standardization procedure described by Waring and Annell (1951) was adopted (see Procedure).

Because the complete spectrum coverage of the prism spectrograph for a single exposure makes available the K lines at 7665 and 7699 Å and the Na lines at 5890 and 5896 Å, it is possible to detect K and Na as low as 0.1 percent in 1 mg samples. This is a distinct advantage, especially in seeking to differentiate between various uranium minerals, such as carnotite and tyuyamunite (table 4). In addition the Ca lines at 8498, 8542, and 8662 Å are available. As many of the samples submitted for analysis contain high concentrations of uranium, these lines are useful because their intensities are not depressed by uranium nearly as much as are those of the Ca lines at 3159 and 3179 Å.

The use of standard solutions, involving only one element per plate and producing relatively simple spectrograms, greatly facilitated the selection of reliable analytical lines (table 2). The accuracy of the method depends upon the utilization of the proper lines (see Results and tables).

Checks of many of the X-ray diffraction patterns and some chemical checks, obtained in those few cases where enough sample was available for a chemical microanalysis, have been made (tables 3 and 4). The agreement of the chemical and spectrographic results are adequate for purposes of mineral identification. It has been our experience in applying the method that the agreement is likely to be good for samples weighing about 1 mg; for such samples the results may become semiquantitative rather than qualitative.

Although the standardization of the method is on a semiquantitative basis (Waring and Annell, 1951), the results have been reported only in qualitative terms, defined in Discussion, for the following reasons: (1) many of the samples weigh less than 1 mg, necessitating upgrading of the element concentration estimations with respect to the standard spectrograms that are based on 1 mg of sample; (2) in the case of the X-ray powder spindles the exact weights of the samples are not known; (3) the omission of a flux (Procedure) increases the possibility of the sample matrix influencing a determination; and (4) the number of chemical checks is insufficient for a statistical study of the accuracy of the method.

The dispersion of the medium quartz prism spectrograph used is 4.6 Å/mm at 2500 Å, 8.4 at 3000 Å, 17.2 at 3500 Å, 21.5 at 4000 Å, 42 at 5000 Å, 75 at 6000 Å, and 111.5 at 7000 Å. The low dispersion from 5000 Å up is not troublesome because this region is generally free from strong lines other than those of the alkali elements which are readily resolved.

Another medium quartz prism spectrograph was available having a lower dispersion of 8.7 Å/mm at 2500 Å, 14.8 at 3000 Å, 22.5 at 3500 Å, 33 at 4000 Å, 61 at 5000 Å, 100 at 6000 Å, and 167 at 7000 Å. This spectrograph permits a complete spectrum coverage for a single exposure on a 10-in. plate. Tests were made to determine whether this instrument was also applicable to the microqualitative method in spite of its lower dispersion than the first spectrograph. Under similar excitation, optical, and exposure conditions (Procedure), a plate was exposed to 1 mg samples of four minerals producing complex spectra (carnotite, calcium uranylvanadate, brannerite, and allanite). Then, utilizing the solution method of preparing the standard electrodes, standard plates were made for the elements Ca, K, Na, Fe, Ti, Si, Th, U, V, Ce, La, and Y, constituting the major and minor components of these minerals. The series of spectrograms obtained for each element represented concentrations of 10 percent, 1 percent, and 0.1 percent based on 1 mg of sample. By means of these standard plates, the positions of the analytical lines were readily determined. In spite of the low dispersion of the instrument, no difficulty was experienced in identifying these lines in the complex spectrograms of the "unknown" samples. The analytical results obtained checked with those previously reported for the same samples tested with the prism spectrograph with higher dispersion. It is thus indicated that, in conjunction with the solution standardization procedure, the lower dispersion medium quartz prism spectrograph also can be used effectively for the qualitative analysis of single grains, X-ray spindles, and other small samples weighing 1 mg or less.

Prior to adopting the solution method of standardizing the medium quartz prism spectrographs, the use of pure minerals as standards had been considered. For the following reasons, however, it was adjudged impracticable: (1) the very large number of mineral standards required; (2) the difficulty of obtaining pure minerals; (3) the problem of diluting these minerals to obtain sets of spectrograms corresponding to various series of decreasing element concentrations; (4) the presence of impurities in the unknown samples analyzed and the fact that the samples are often mixtures of two or more distinct minerals; (5) the need for an independent and all-inclusive procedure of analysis in cases where the sample is a newly discovered mineral in the process of identification or where it is a chemical precipitate or other material; and (6) the complexity of the resulting spectrograms thus again making it difficult to select reliable analytical lines.

PROCEDURE

As described by Waring and Annell (1951), the solution standardization procedure involves the preparation of a standard plate for each element, each plate showing a series of spectrograms representing

element percentages decreasing in multiples of ten from 10 percent to 0.0001 percent, based on an unknown sample weighing 1 mg.

The standard solutions are prepared from "C. P." and "Specpure" grade chemicals usually to give a concentration of 10 mg of the element per milliliter of solution (for the compositions); 0.01 ml of each 10 mg/ml solution is equivalent to 10 percent of the element in a 1 mg sample. These solutions are consecutively diluted so that 0.01 ml of each is then equivalent to 1.0, 0.1, 0.01, 0.001, and 0.0001 percent of element based on a 1-mg sample.

In the preparation of a series of standard electrodes representing 10-0.0001 percent element concentrations in a 1-mg sample, the bottoms of the electrode craters are first sealed with paraffin added in the form of a few drops of a 1 percent benzene solution of the wax (Waring and Annell, 1951). Then 0.01-ml aliquots of the 10-0.0001 mg/ml solutions are introduced into the electrodes, using a micropipette equipped with an extension whose tip fits into the craters. The electrodes are dried in a brass holder placed on an asbestos-covered hot plate adjusted to a temperature of approximately 100 C.

Provision of reference spectra for the standard plates follows the arrangement used by Waring and Annell (1951). Before arcing of the electrodes in the order of decreasing element concentration, a spectrum of iron is recorded on the plate. Following arcing of the last standard electrode, a spectrum of 1 mg of aluminum alloy (Alcoa aluminum standard no. 874) weighed out in the form of filings is also registered. The spectrograms are 2.3 mm high and positioned so that the bottom of one spectrogram nearly coincides with the top of the succeeding one. The arrangement is similar for the unknowns except that the number of spectrograms included between the reference spectra is limited to two or three. In running a suite of unknowns, a half dozen such series of spectrograms and reference spectra can be recorded on a plate.

The concentrations of elements in the unknown samples are estimated by visual comparison of certain lines of these elements in the unknown spectrograms with those on the standard plates. Where the sample weight is less than 1 mg, the estimations are upgraded by the necessary factor. If, for example, the sample weighs 0.5 mg, the preliminary estimations are multiplied by two. The plates are read on a viewing desk under a microscope or on a viewing box with a magnifying eyepiece.

Besides furnishing reference points additional to those provided by the iron spectrum, the aluminum alloy spectrum serves as a useful check on exposure, emulsion speed, and plate processing. The Cr line at 2780.703 Å, in particular, is a sensitive indicator of the optimum conditions. When these are being maintained, the intensity of the line falls within a transmission range of 80 to 95 percent, measured with a Jarrell-Ash microphotometer. The other components of the alloy--Cu, Fe, Mg, Mn, Si, Ti, and Zn--present in known trace amounts also produce lines whose intensities may conveniently be used for supplementary reference when estimating concentrations of these elements in the unknowns.

The power for the d-c arc is supplied by a full-wave mercury vapor rectifier (220 volts direct current and 15 amp maximum). An inductance for giving smooth operation of the arc and a rheostat for controlling the current are used in series with the arc. The rheostat has three fixed values, 74, 38, and 19 ohms, producing three possible arc currents of approximately 2, 4, and 9 amp. The value of the inductance is not critical; in this case an old 7.5-kw autotransformer is used for the purpose.

The standard electrodes, the aluminum alloy samples, and the unknowns are arced at 9 amp. The iron arc is operated at 4 amp. All arcings are with a gap of 4 mm for a period of 60 seconds at 8 percent transmission controlled by a rotating-sector disk. The slit width is 10 microns, with the arc focused on the collimating lens. The emulsion used is Eastman I-L, developed in D-19 for 4 minutes at 18 C + 1/2 C.

The samples are weighed on a 5-mg torsion microbalance and generally range from 0.1 to 1 mg. A microfunnel drawn from 7-mm glass tubing is used to transfer the samples from the detachable balance pan to the electrode craters. Spindles are transferred directly by sliding them off the pan.

The weight of sample in a spindle is determined approximately by subtracting from the total weight of the spindle and its contents the estimated weight of the spindle alone. Spindle weights can be estimated to within about + 0.1 mg by comparison with an available series of previously weighed blank spindles. A supplementary criterion for estimating the weight of sample in a spindle is the fact that usually the weight ratio of spindle to sample is about 1:1. As spindles and their contents usually weigh from 0.5 to 1 mg, the actual sample weight ranges from 0.25 to 0.5 mg.

No powdered graphite or other flux is added to the sample because the nature of the samples precludes effective mixing.

The determination of fluorine in the samples of low calcium content requires a separate exposure (Waring and Annell, 1952). Two-tenths of a milligram of calcium as calcium chloride in solution is added to the electrodes that are dried before introduction of the unknown samples. The addition of calcium causes the formation in the arc of the calcium fluoride molecule that emits the bands used for the fluorine estimation.

The carbon microelectrode used has a deep, thin-walled, cylindrical crater that is convenient for the loading and arcing of X-ray powder spindles, in addition to other materials. The half-inch depth of the crater corresponds to the length of the average spindle, thereby eliminating any necessity for cutting it up. This depth also tends to prevent mechanical loss during arcing of the sample when it consists of refractory grains. After fusing, the sample adheres to the graphite and burns away to completion along with the carbon, thus fulfilling an essential requirement of qualitative analysis (Nachtrieb, 1950). The dimensions of the electrode,

cut and drilled with a Bausch and Lomb electrode shaper, are as follows:

1/8-in. spectroscopic carbon rod.	1 3/4 in. long
Crater, outside diameter.....	0.090 in.
Crater, inside diameter.....	0.052 in. (no. 55 drill)
Crater, depth.....	1/2 in.
Outside shoulder below crater rim.	5/8 in.

The upper electrode, the cathode, is cut from a 1/4-in. spectroscopic carbon rod. Its arc end is hemispherical with a 0.06-in. radius. Tests showed that this upper electrode produces less background in the spectrograms than would be caused by electrodes of smaller dimensions.

The iron arc arrangement consists of a 1/4-in. iron rod as the lower positive electrode and an upper carbon electrode the same as that used for the samples.

RESULTS AND TABLES

Table 1 lists the sensitivities on the basis of 1-mg samples for the 69 elements determined with the method. The values are those indicated by the solution standard plates on the basis of 1 mg of sample. Where less than 1 mg of sample is available, the sensitivities are reduced by a factor equal to that applied in upgrading the estimations of element concentrations (Procedure). Interference by the lines of other elements also decreases the sensitivities listed. For example, where uranium is a major or minor component of a sample, the thorium line at 2837.299 Å cannot be used because of interference by uranium lines at 2837.328 and 2837.187 Å. The less sensitive thorium lines at 2703.962 and 2565.597 Å then must be utilized, thus reducing the visual detection limit of thorium from 0.1 percent to 1 percent. The maximum sensitivities of Al, B, Ca, Cu, Li, Mg, Si, Ti, and V are limited by the presence of these elements as residual impurities in the regular grade carbon electrodes. The method is not designed for extreme sensitivity but rather for a means by which major and minor concentrations of 68 elements in small samples may be checked in one exposure.

Table 2 lists the wavelengths (Harrison, 1939) and individual sensitivities of the analytical lines used. Wherever practicable two or more lines are listed for each of the major, minor, and trace concentration ranges reported. In spectrographic quantitative analysis the utilization of various lines for different ranges of element concentrations is necessary (Harrison and others, 1948); in a qualitative method the use of such lines in addition to the persistent lines is advisable, especially where the concentration of an element lies on or close to the boundary of demarcation between percentage brackets. The choice of the lines was guided by the various tables in the literature (Waring and Annell, 1952; Waring and Mela, 1952; Harrison, 1939; Brode, 1943; Harvey, 1947), by considerations of freedom from interference by the lines of closely associated elements, and by checks of the solution standard plates with spectrograms of 1-mg samples of National Bureau of Standards standard samples and other standards

available. Owing to interference by the cyanogen bands, a number of persistent lines cannot be used, for instance those of K at 4047 and 4044 Å and of In at 4511 Å.

Table 3 lists the results of chemical micro-analyses of some samples originally analyzed by the spectrographic microqualitative method. These samples were available in amounts of only a few milligrams, and the qualitative spectrographic results shown were intended to serve as a guide for the subsequent quantitative chemical analyses. Comparison of the 31 determinations of 13 elements in the eight samples indicates seven disagreements of the spectrographic results with the chemical in the magnitude of one percentage bracket. These disagreements were not considered too serious because it was still possible to identify the minerals from the data at hand.

Table 4 lists a number of the mineral identifications of small single-grain samples that have been accomplished by agreement of the spectrographic microqualitative analyses with the data from the X-ray diffraction patterns. The spectrographic determinations of more than 40 different elements have thus been checked on a qualitative basis.

The compositions of the standard solutions (Waring and Annell, 1952) are tabulated on pp. 14-16.

FUTURE PROGRAM

Plans for further improvement of the micro-qualitative method include an investigation of the possible application of a controlled arc atmosphere designed to eliminate the cyanogen bands obscuring a large number of persistent lines. The sensitivities for elements such as Cs, Rb, Th, U, and many rare earths might thus be increased. The preparation of standard spectrograms on the basis of 0.5 mg of sample rather than 1 mg, involving the dilution by a factor of two of the present standard solutions, is also being considered. Such spectrograms, by representing a sample weight closer to that usually used, would aid in making the method more nearly semiquantitative.

LITERATURE CITED

- Brode, W. R., 1943, *Chemical spectroscopy*, 2d ed., New York, John Wiley and Sons, Inc.
- Harrison, G. R., 1939, *M. I. T. wave-length tables*, New York, John Wiley and Sons, Inc.
- Harrison, G. R., Lord, R. C., and Loofbourow, J. R., 1948, *Practical spectroscopy*, New York, Prentice-Hall, Inc., pp. 457-458.
- Harvey, C. E., 1947, *A method of semi-quantitative spectrographic analysis*, Glendale, Calif., Applied Research Laboratories.
- Jaffe, Howard, 1949, *Visual arc spectroscopic detection of halogens, rare earths and other elements by use of molecular spectra: Am. Mineralogist*, vol. 34, pp. 667-674.
- Lee, O. I., and Wright, T. A., 1939, *On identifying minerals with the aid of the spectrograph: Proc. 6th Summer Conference on spectroscopy and its application*, New York, John Wiley and Sons, Inc.
- Nachtrieb, N. H., 1950, *Principles and practice of spectrochemical analysis*, pp. 235-237, New York, McGraw-Hill Book Co., Inc.

Peterson, M. J., Kauffman, A. J., Jr., and Jaffe, H. W., 1947, The spectroscope in determinative mineralogy: *Am. Mineralogist*, vol. 32, pp. 322-335.

Tongeren, W. van, 1938, Contributions to the knowledge of the chemical composition of the earth's crust in the East Indian Archipelago. I. The spectrographic determination of the elements according to arc methods in the range 3600-5000 A. II. On the occurrence of rarer elements in the Netherlands East Indies, D. B. Centen's, Amsterdam.

Waring, C. L., and Ansell, C. S., 1951, A semi-quantitative spectrographic method for the analysis of minerals, rocks, and ores: U. S. Geol. Survey Trace Elements Inves.Rept. 143. [Unpublished.]

1952, A semiquantitative spectrographic method for the analysis of minerals, rocks, and ores (II): U. S. Geol. Survey Trace Elements Inves.Rept. 215. [Unpublished.]

Waring, C. L., and Mela, Henry, Jr., 1952, the determination of small amounts of rare earths in phosphate rocks: U. S. Geol. Survey Trace Elements Inves.Rept. 239. [Unpublished.]

Table 2.--Wavelengths and sensitivities of the analytical lines used in the microqualitative method--Continued

Element	Wavelength (A)	Sensitivity (percent)	Element	Wavelength (A)	Sensitivity (percent)
Co-----	3453.505	1.0	Gd-----	3100.508	0.1
	3412.633	1.0		3034.059	1.0
	3412.339	1.0		3032.850	1.0
	3044.005	1.0		3027.612	1.0
	2521.363	1.0		2840.236	10.0
	2663.529	10.0		2809.720	10.0
	2649.940	10.0			
	2519.822	10.0	Ge-----	3039.064	.1
Cr-----	4289.721	.1		2651.575	.1
	4274.803	.1		2651.178	.1
	4254.346	.1		3269.494	1.0
	2843.252	.1		2691.344	1.0
	2835.633	.1		2740.431	10.0
	2860.934	1.0		2589.188	10.0
	2855.676	1.0	2533.229	10.0	
	2769.915	10.0	Hf-----	3134.718	.1
	2731.908	10.0		3072.877	.1
Cs-----	8521.10	10.0		3012.902	.1
				2861.696	1.0
				2861.012	1.0
Cu-----	3273.962	.001		2683.353	10.0
	3247.540	.001		2531.193	10.0
	2618.366	1.0	Hg-----	2536.519	1.0
	2492.146	1.0		3131.833	10.0
	2766.371	10.0		3131.546	10.0
	2441.637	10.0		3125.663	10.0
Dy-----	3407.80	1.0	Ho-----	3456.00	.1
	3393.583	1.0		3453.13	1.0
	3385.027	1.0		3416.46	1.0
	3280.10	1.0		3398.98	1.0
	3251.260	1.0			
Er-----	3264.781	.1	In-----	3256.090	.1
	3230.585	.1		3039.356	.1
	2964.518	1.0		3258.564	1.0
		2753.878		10.0	
		2710.265		10.0	
Eu-----	2813.95	.1	Ir-----	3220.780	1.0
	2906.676	1.0		2639.712	1.0
	2727.780	1.0		2543.971	1.0
	2685.65	10.0		2534.457	10.0
	2678.28	10.0		2533.131	10.0
F----- (CaF band heads)	6064.4	1.0	K-----	7698.979	.1
	6036.9	1.0		7664.907	.1
	5291.0	10.0	La-----	3337.488	.1
Fe-----	3020.640	.1		3344.560	1.0
	2599.396	.1		3303.11	1.0
	2739.546	1.0		3265.67	1.0
	2598.369	1.0		2808.39	10.0
	3100.304	10.0		2610.335	10.0
	3099.971	10.0			
	3099.897	10.0			
Ga-----	2943.637	.1	Li-----	6707.844	.01
	2944.175	1.0		6103.642	1.0
	2874.244	1.0		3232.61	1.0
	2719.653	10.0		2741.31	10.0
	2500.173	10.0			

Table 2.--Wavelengths and sensitivities of the analytical lines used in the microqualitative method--Continued

Element	Wavelength (A)	Sensitivity (percent)	Element	Wavelength (A)	Sensitivity (percent)	
Lu-----	3077.60	0.1	Pb-----	2833.069	0.1	
	2615.42	.1		2802.003	.1	
	2619.26	1.0		2614.178	.1	
	2613.40	1.0		2873.316	1.0	
	2685.08	10.0		2823.189	1.0	
	2392.19	10.0		2663.166	1.0	
Mg-----	2852.129	.001	Pd-----	2393.794	10.0	
	2802.695	.001		3421.24	.1	
	2795.53	.001		3242.703	.1	
	2782.974	1.0		3251.640	1.0	
	2779.834	1.0		2763.092	1.0	
	2776.690	1.0		3002.652	10.0	
Mn-----	2576.104	.01	Pr-----	2922.492	10.0	
	2605.688	.1		4241.019	1.0	
	2593.729	.1		4225.327	1.0	
	2939.304	1.0		5322.778	10.0	
	2933.063	1.0		5259.743	10.0	
	3044.567	10.0		Pt-----	3064.712	.01
2584.308	10.0	2997.967	.1			
Mo-----	3193.973	.1	2659.454		.1	
	3170.347	.1	2650.857		1.0	
	2816.154	.1	2646.886		1.0	
	3208.834	1.0	2803.239		10.0	
	3158.165	1.0	2639.350	10.0		
	2784.992	10.0	Rb-----	7947.60	1.0	
2763.620	10.0	7800.227		1.0		
Na-----	5895.923	.1		Re-----	3464.722	1.0
	5889.953	.1			3460.47	1.0
	3302.988	10.0			2715.470	10.0
	3302.323	10.0			2674.337	10.0
Nb-----	3225.479	.1	Rh-----	3434.893	.1	
	3094.183	.1		3396.85	1.0	
	2931.469	1.0		3283.573	1.0	
	2876.947	1.0		3280.55	1.0	
	2875.392	1.0		3271.612	10.0	
	2746.104	10.0		3263.144	10.0	
Nd-----	2745.729	10.0	Ru-----	2874.984	1.0	
	4303.573	1.0		2735.718	1.0	
	4247.367	1.0		2678.758	1.0	
	3328.270	10.0		2886.536	10.0	
Ni-----	3275.218	10.0	Sb-----	2734.349	10.0	
	3050.819	.1		2598.062	.1	
	3002.491	.1		2877.915	1.0	
	2992.595	1.0		2769.939	1.0	
	2943.914	1.0		2718.893	10.0	
	2907.459	10.0		2670.643	10.0	
Os-----	2798.653	10.0	Sc-----	2560.227	.1	
	3058.66	1.0		2552.359	.1	
	2909.061	1.0		2555.799	1.0	
	3301.559	10.0		2545.204	1.0	
P-----	2838.626	10.0	2822.131	10.0		
	2553.28	1.0				
	2535.65	1.0				
	2554.93	10.0				
2534.01	10.0					

Table 2.--Wavelengths and sensitivities of the analytical lines used in the microqualitative method--Continued

Element	Wavelength (A)	Sensitivity (percent)	Element	Wavelength (A)	Sensitivity (percent)
Si-----	2881.578	0.01	Tm-----	3133.89	.1
	2516.123	.01		3131.26	.1
	2987.648	1.0		4242.15	1.0
	2435.159	1.0		3462.20	1.0
	2532.378	10.0		3362.61	1.0
	2438.782	10.0			
Sm-----	3273.477	1.0	U-----	4244.372	1.0
	3272.803	1.0		4241.669	1.0
	3254.378	1.0		2882.741	1.0
	3254.290	1.0	V-----	3185.396	.1
	3253.931	1.0		3183.982	.1
Sn-----	3034.121	.1	3183.406	.1	
	2839.989	.1	3202.381	1.0	
	3009.147	1.0	3198.012	1.0	
	2863.327	1.0	3214.750	10.0	
	2850.618	1.0	3212.434	10.0	
	2661.248	10.0	W-----	2946.981	1.0
	2571.592	10.0		2944.395	1.0
		2947.384		10.0	
		2589.167		10.0	
Sr-----	4607.331	1.0	Y-----	3242.280	.01
	3464.457	1.0		3216.682	.01
	4305.447	10.0		3200.270	.1
	3380.711	10.0		3195.615	.1
Ta-----	2685.11	.1	2984.256	1.0	
	2635.929	.1	2422.185	1.0	
	2714.674	1.0	3086.858	10.0	
	2675.901	1.0	3055.22	10.0	
	2902.046	10.0	Yb-----	3289.37	.01
	2891.843	10.0		2970.564	.1
		3031.11		1.0	
		2653.75		1.0	
Tb-----	4278.51	1.0	3107.897	10.0	
	3324.40	1.0	Zn-----	3345.020	1.0
	3219.95	1.0		3302.588	1.0
	3218.93	1.0		3282.333	1.0
		2800.869		1.0	
		4810.534		10.0	
		2770.984		10.0	
Te-----	2385.76	1.0	2770.865	10.0	
	2383.25	1.0	Zr-----	3438.230	.1
		3391.975		.1	
		2758.813		1.0	
		2752.206		1.0	
		2889.430		10.0	
Th-----	2837.299	.1	2888.036	10.0	
	2832.319	.1			
	2870.413	1.0			
	2842.815	1.0			
	2703.962	1.0			
	2565.597	1.0			
	4391.114	10.0			
	Ti-----	3241.986	.01		
		3239.038	.01		
		3236.573	.01		
		3234.516	.01		
3088.025		.01			
3078.645		.1			
3072.971		.1			
3072.107		.1			
2956.131		1.0			
2941.995		1.0			
2619.939		10.0			
2605.151		10.0			
Tl-----		2767.87	1.0		
	5350.46	10.0			
	2918.32	10.0			

Table 3.--Comparison of chemical^a quantitative and spectrographic^b qualitative microanalyses of samples of uranium minerals

[Columns 1-6, (TWC 2050, TWS 712, lot 3218), columns 1-8, (TWX 319)]

Element	Kasolite		Uranophane		Cuprosklodowskite		Soddyite	
	Chemical (percent)	Spectro-graphic						
	1		2		3		4	
Al-----	---	---	---	---	---	---	---	---
Ca-----	0.71	Trace	7.3	Minor	---	---	---	---
Cu-----	---	---	---	---	5.3	Minor	---	---
Fe-----	---	---	---	---	---	---	---	---
Mg-----	---	---	---	---	---	---	---	---
Pb-----	29.0	Major	---	---	---	---	---	---
Si-----	4.9	Major	6.2	Major	4.8	Major	4.1	Major
Th-----	---	---	---	---	---	---	---	---
Ti-----	---	---	---	---	---	---	---	---
U-----	43.5	Major	50.8	Major	53.2	Major	68.0	Major
V-----	---	---	---	---	---	---	---	---
Er-----	---	---	---	---	---	---	---	---
Y-----	---	---	---	---	---	---	---	---
Rare earths-----	---	---	---	---	---	---	---	---

Element	Beta-uranotil		Sklodowskite		Brannerite		Calcium uranylvanadate	
	Chemical (percent)	Spectro-graphic	Chemical (percent)	Spectro-graphic	Chemical (percent)	Spectro-graphic	Chemical (percent)	Spectro-graphic
	5		6		7		8	
Al-----	---	---	---	---	---	---	0.2	Trace
Ca-----	5.2	Minor	2.5	Minor	2.0	Trace	4.5	Minor
Cu-----	---	---	---	---	---	---	---	---
Fe-----	---	---	---	---	1.8	Minor	---	---
Mg-----	---	---	1.3	Minor	---	---	---	---
Pb-----	---	---	4.9	Minor	---	---	---	---
Si-----	6.1	Major	6.5	Major	0.23	Trace	---	---
Th-----	---	---	---	---	4.4	Minor	---	---
Ti-----	---	---	---	---	19.7	Major	---	---
U-----	49.3	Major	50.3	Major	33.8	Major	49.3	Major
V-----	---	---	---	---	---	---	12.2	Major
Er-----	---	---	---	---	---	Minor	---	---
Y-----	---	---	---	---	---	Trace	---	---
Rare earths-----	---	---	---	---	6.5	---	---	---

^aChemical results = oxides reduced to elements.

^bMajor, approximately 10 percent or more; Minor, approximately 1-10 percent; and Trace, approximately 0.1-1 percent.

¹Belgian Congo; lab. no. 75083.

²Yancey, N. C.; lab. no. 75084.

³Jachymov, Bohemia; lab. no. 75085.

⁴Belgian Congo; lab. no. 75086.

⁵Jachymov, Bohemia; lab. no. 75087.

⁶Belgian Congo; lab. no. 75088.

⁷Dean's mine, Mono County, Calif.; lab. no. 66779; lot no. 595; (TWC 1959, TWS 569).

⁸Small Spot mine, Mesa County, Colo.; sample no. JJK/1/52; lot no. 0-22; (TWC 2052; TWS 786).

Table 4.--Mineral identifications accomplished by agreement of spectrographic microqualitative analyses with data from X-ray diffraction patterns

Sample no.	Lot no.	Trace Elements X-ray film no.	Mineral identification	TWS report	Spectrographic analyses ¹		
					Major	Minor	Trace
Minerals for standard X-ray patterns							
EC-52-----	0-70	2286	Azurite-----	738	Cu	---	Si Al
EC-53-----	0-70	2287	Chrysocolla-----	738	Cu Si	Al	Mg
EC-54-----	0-70	2293	Apophyllite-----	738	Ca Si	K F	Al Na
EC-56-----	0-70	2294	Cerussite-----	738	Pb	---	Ca
EC-59-----	0-70	2313	Franklinite-----	738	Zn	Fe Mn	Al
EC-64-----	0-70	2314	Pyrargyrite-----	738	Ag Sb	Si	Zn Cu
EC-65-----	0-70	2315	Realgar-----	738	As	---	Ca
EC-76-----	0-70	2283	Talc-----	738	Mg Si	---	Fe Al
Uranium-bearing minerals							
FK-26F-----	1193	1986	Quartz and carnotite-----	549	Si	U V Mg Fe	Na K Al
YC-1-51-----	1635	1975	Tyuyamunite and clay(?)-----	542	U V Si	Ca Al Fe	Mg Cu
J-59-----	1128	2389	Calcium uranylvanadate-----	770	U V	Ca Si Na	Mg Al
ADW-170-----	0-20	1919	Rauvite-----	533	U V	Ca	Al Ti Ba Si
T-38a-----	1128	2476	Rauvite and quartz-----	789	U Si V	Ca	Al Na Fe
DN-31A-----	1708	2067	Uranophane and phosphuranylite-----	597	U Si	Ca Al Na K P As	Mg
J-102C-----	1128	2424	Autunite-----	774	U	P Ca Si Na	Cu Mg Fe Ba Al
CS-3-4-1(1)-	1629	2244	Autunite-uranocircite-----	677	U	P Si Ba Ca	Na Fe Mg Al
J-103-----	1128	2409	Autunite, saleeite, and torbernite-----	774	U P Ca	Mg Si Na	Cu Al Fe
J-81-----	1128	2346	Zeunerite-----	770	U As	Cu Ba Si	Na
J-102B-----	1128	2423	Torbernite-----	774	U	P Cu Si Ca Na	Fe Mg As K Ba Al
4493-C(3)---	551	2251	Uraninite and smaltitecloanthite-----	690	U	Si As Co Ni Fe Ba	Cu Na Y Al Mg
2904-G(1)---	551	2405	Huttonite-----	761	Th Si U	Ca Fe Na	Pb K B Mg Al Mn
4419-H(3)---	551	2166	Brannerite, thorite, and samarskite-----	727	Th Ti	U Si Nb Y	Fe Bi Na Ni Ca
Rare-earth minerals							
JNS-2-----	0-1	2498	Allanite-----	778	Si Fe	Al Ce La Ca Na Mg Th Nd Pr	Mn K
P-59-Ba-----	0-51	1692	Bastnaesite-----	522	Ce	La Y Ca Al Fe Si P	Mg Mn Pb Th

5

51P-72a-----	1613	2266	Florencite-----	687	P Al Ce	Si Th La Fe Ca Zr	Tl Gd Pb Y Ba K
51P-72b-----	1613	2272	Florencite and rutile-----	687	P Ti	Si Ce Al Zr La	Th Pb Fe K Ba Y Ca
4428----- U.S.N.M. no. 80183 ²	3036 0-70	2192 B-255 and B-256 ³	Parisite----- Cyrtolite-----	658 746	Ce La Zr Si Hf	Ca Nd Y Fe Ca	Fe U Mn Th Na Al Yb Gd B

Miscellaneous minerals

J-102A-----	1128	2426	Quartz and hydromica-----	774	Si	K Fe Al Mg Na	Ca Ti
W-88-----	1128	2477	Kaolinite-----	789	Si Al	K Mg Na	Ca Fe Ti
AT-20-----	1126	2367	Gibbsite-----	757	Si Al	Na	Mg Ca K Cu Fe Ni
4099-----	3035	2043	Topaz and impurities-----	576 and 579 778	Al Si	F Pb	Ca Fe
JNS-1-----	0-1	2479	Biotite-----	778	Si Fe	Al Mg K Ca Na	Li Ti
J-56-----	1128	2377	Apatite and hydromica-----	770	Ca Si	Fe Mg K P Al Na	Mn V Ti Ba
ADW-173-----	0-20	1922	Hewettite-----	533	V	Ca	Ti Ba Si
4477-A-----	551	2148	Melanovanadite, quartz, and barite(?)---	723	V	Ca Si Ba	Fe Mg Na Ti Al
51-AWe-107--	3035	2023	Vosenite-----	571	Fe Mg B	Mn Si	Ca Na Ti Ni
51-P-67-----	1613	2246	Hematite, rutile, and ilmenite-----	687	Fe Ti	Si Mn	Na Mg Al Ca
51-P-67m----	1613	2241	Magnetite-----	687	Fe	Si Na	Ti Mg Al Mn Ca
J-102D-----	1128	2393	Goethite-----	770	Fe	Si Na	Cu Ca Al K Mg
ADW-186-----	0-20	1913	Conichalcite and quartz-----	561	Cu Ca As Si	V	Al Mg Mn Ba
4385-----	3036	2193	Orpiment-----	655	As	---	Al Mn Si Ti V
K-35-3-----	1637	2486	Sphalerite-----	787	Zn Si	Mg Na	K
WE-186A-----	3035	2196	Pyrochlore-microlite-----	654	Ca Ta	Nb Na	Fe Mn Si Ti

¹Major, approximately 10 percent or more; Minor, approximately 1-10 percent; and Trace, approximately 0.1-1 percent.

²U. S. National Museum sample no.

³U. S. National Museum X-ray film no.

COMPOSITION OF STANDARD SOLUTIONS

(Waring and Annell, 1952)

The following standard solutions were made from compounds and elements available in the laboratory. The compounds were dissolved in distilled water unless otherwise noted.

Element standardized	Compound used	Solution
Ag	AgNO ₃ , reagent-----	
Al	AlCl ₃ .6H ₂ O, C. P.-----	Compound dried in oven at 140 C and dissolved in cold acidified H ₂ O.
As	As ₂ O ₃ , Nat. Bur. Standards no. 83a.	1:1 HNO ₃ , heated. Diluted to volume with H ₂ O.
Au	Au, metal-----	Aqua regia. Boiled down several times with HCl (conc) to drive off HNO ₃ . Diluted to volume with H ₂ O.
B	H ₃ BO ₃ , C. P.-----	
Ba	BaCl ₂ .2H ₂ O, C. P.-----	
Be	Be, metal-----	Dilute HCl.
Bi	Bi, metal-----	1:1 HNO ₃ , diluted to volume with H ₂ O.
Ca	CaCl ₂ .2H ₂ O, anal. reagent--	
Cd	CdCl ₂ .2½H ₂ O, C. P.-----	
Ce	CeO ₂ -----	H ₂ SO ₄ , (conc) heated to form amber, Ce(SO ₄) ₂ . 6 percent H ₂ SO ₃ added to form colorless Ce ₂ (SO ₄) ₃ . Diluted to volume with H ₂ O.
Co	CoCl ₂ .6H ₂ O, C. P.-----	
Cr	Cr, metal-----	1:1 H ₂ SO ₄ .
Cs	CsCl, C. P.-----	
Cu	CuO, reagent-----	Dilute HCl.
Dy	Dy ₂ O ₃ -----	1:1 HCl. Diluted to volume with H ₂ O.
Er	Er ₂ O ₃ -----	1:1 HCl. Diluted to volume with H ₂ O.
Eu	Eu ₂ O ₃ -----	1:1 HCl, heated. Diluted to volume with H ₂ O.
F	CaCl ₂ , C. P. and NaF, C. P.	H ₂ O (2 solutions).
Fe	Fe, metal-----	Dilute H ₂ SO ₄ .
Ga	Ga, metal, C. P.-----	Aqua regia. Diluted to volume with H ₂ O.
Ge	GeO ₂ , C. P.-----	HF, 48 percent. H ₂ SO ₄ (conc), added and heated to drive off HF. Diluted to volume with H ₂ O.
Gd	Gd ₂ O ₃ -----	Dilute HCl.
Hf	HfO ₂ -----	Dilute H ₂ SO ₄ , heated and H ₂ O ₂ , 3 percent, added until dissolved. Diluted to volume with H ₂ O.
Hg	HgCl ₂ , reagent-----	
Ho	Ho ₂ O ₃ -----	1:1 HCl, heated. Diluted to volume with H ₂ O.
In	In, metal-----	HNO ₃ , conc. Diluted to volume with H ₂ O.

Element standardized	Compound used	Solution
Ir	Ir metal powder, C. P. -----	Fused with 3 parts KOH and 1 part KNO ₃ . Fusion dissolved in aqua regia. SiO ₂ filtered off. Filtrate boiled down to small volume. Crystals of K ₂ IrCl ₆ separate upon cooling and dissolve in H ₂ O.
K	HKC ₈ H ₄ O ₄ , Nat. Bur. Standards.	
La	La ₂ O ₃ -----	Dilute HCl.
Li	Li ₂ CO ₃ , reagent -----	Dilute HCl.
Lu	Lu ₂ O ₃ -----	1:1 HCl, heated. Diluted to volume with H ₂ O.
Mg	Mg, metal -----	Dilute HCl.
Mn	MnCl ₂ .4H ₂ O, C. P. -----	
Mo	Mo, metal -----	Aqua regia, heated. Diluted to volume with H ₂ O.
Na	NaCl, reagent -----	
Nb	Nb, metal -----	48 percent HF. Diluted to volume with HNO ₃ , conc.
Nd	Nd ₂ O ₃ -----	1:1 HCl. Diluted to volume with H ₂ O.
Ni	Ni, metal -----	1:1 HNO ₃ , heated. Diluted to volume with H ₂ O.
Os	Os metal powder, C. P. -----	Os metal powder heated with aqua regia in flask fitted with reflux condenser.
P	NaH ₂ PO ₄ .H ₂ O, C. P. -----	
Pb	Pb(NO ₃) ₂ , C. P. -----	
Pd	Pd, wire -----	Aqua regia. Diluted to volume with H ₂ O.
Pr	Pr ₆ O ₁₁ -----	1:1 HCl. Diluted to volume with H ₂ O.
Pt	Pt, sheet -----	Aqua regia. Boiled down several times with HCl, (conc) to drive off HNO ₃ . Diluted to volume with H ₂ O.
Rb	RbCl -----	
Re	Re, metal -----	HNO ₃ , conc. Diluted to volume with H ₂ O.
Rh	RhCl ₃ , dry, C. P. -----	Dilute HCl.
Ru	(NH ₄) ₂ RuCl ₅ -----	Hot H ₂ O.
Sb	SbI ₃ , C. P. -----	Acetone + HCl, dil.
Sc	Sc ₂ (SO ₄) ₃ .5H ₂ O -----	
Si	SiO ₂ , pure -----	Na ₂ CO ₃ fusion. Diluted to volume with H ₂ O.
Sm	Sm ₂ O ₃ -----	Dilute HCl.
Sn	SnCl ₂ .2H ₂ O, reagent -----	
Sr	SrCO ₃ , reagent -----	Dilute HCl.
Ta	Ta, metal -----	48 percent HF + HNO ₃ , conc. Diluted to volume with H ₂ O.
Tb	Tb ₄ O ₇ -----	1:1 HCl, heated. Diluted to volume with H ₂ O.
Te	H ₂ TeO ₄ .2H ₂ O, C. P. -----	1:6 HNO ₃ , heated.

Element standardized	Compound used	Solution
Th	Th(NO ₃) ₄ ·4H ₂ O, C. P. -----	
Ti	TiO ₂ , C. P. -----	48 percent HF + H ₂ O ₂ . H ₂ SO ₄ , (conc), added and heated to drive off HF. Diluted to volume with H ₂ O.
Tm	Tm ₂ O ₃ -----	1:1 HCl, heated. Diluted to volume with H ₂ O.
Tl	TlNO ₃ , C. P. -----	
U	(UO ₂)(C ₂ H ₃ O ₂) ₂ ·2H ₂ O C. P.	
V	NH ₄ VO ₃ , C. P. -----	1:1 HCl. Diluted to volume with H ₂ O.
W	W, metal-----	48 percent HF + HNO ₃ , (conc), heat. Diluted to volume with H ₂ O.
Y	Y ₂ O ₃ -----	1:1 HCl and heat. Diluted to volume with H ₂ O.
Yb	Yb ₂ O ₃ -----	1:1 HCl, heated. Diluted to volume with H ₂ O.
Zn	ZnO, reagent-----	Dilute HCl.
Zr	ZrOCl ₂ ·8H ₂ O, C. P. -----	