OFFICIAL FILE COPY
DMEA
RECEIVED JUN 9 1958

DATE	INITIALS	CODE

ORE RESERVES AND GEOLOGY OF THE WELLBORN THORIUM PROPERTIES

BEAVERHEAD COUNTY, MONTANA

FOR

C. ANDRADE, III
Tower Petroleum Building
Dallas, Texas

BY

WARREN R. WAGNER
6526 Holiday Dr.
Boise, Idaho

Five (5) Copies: No. 1,3 & 4 to Andrade; No. 2, C.H. Kerr, Union Carbide, No. 5, file copy W.R. Wagner.

WARREN R. WAGNER
GEOLOGIST
6526 HOLIDAY DRIVE
BOISE, IDAHO
PHONE 4-1925

4/24/57

SERVING THE MINING, CHEMICAL AND CONSTRUCTION INDUSTRIES

Mr. C. Andrade, III
Tower Petroleum Building
Dallas, Texas

Dear Mr. Andrade:

As you requested, I have made an examination and evaluation of the Wellborn Thorium Properties near Armstead, Montana, and my report is attached.

As you know, the thorium market is limited. "Know How" in the processing and marketing is also scarce. From our telephone conversations, I gather that you have connections with some of the major chemical companies. I think your best bet for turning a thorium property into profit will be through cooperation with one of these.

The Last Chance-Shady Tree ore body on the Wellborn property is one of the most presistent I have ever encountered. The reserves and grade should be of interest to anyone in or contemplating entering the thorium field.

As to the europium content, that will have to await assay returns some two or three weeks from now.

Sincerely yours,
Warren R. Wagner
Warren R. Wagner.

S U M M A R Y

The Wellborn Thorium Property near Armstead, Montana, have an ore reserve conservatively estimated to be 720,000 tons of 0.685 pe cent ThO_2 (thoria), within the first 300 feet of depth. The ore can be mined, concentrated (by gravity) and put on cars at Armstead, for about $20.00 per ton. At $60.00 per unit of ThO_2, the ore is worth $41.10 per ton at the mine; this price, less mining, concentration and trucking costs leaves $21.10 per ton for profit and marketing. Should the ore not be amenable to gravity concentration, then chemical treatment would be needed and the cost per ton of concentrating would rise by at least 50 percent. In this case, serious consideration should be given to the production of thorium salts and/or thorium metal at Armstead, Montana.

The market for thorium is limited and each operator apparently has to make his own. If chemical treatment to produce thorium salts and/or metal is necessary, then, the investment in plant facilities is considerable (probably about $1,500,000.00 for 500 tons per year capacity).

Europium has been reported on the property, but assay returns are not back to confirm this; at any rate, the europium market is less assured than the thorium market.

In conclusion, it is recommended that beneficiation tests be run on the ore before further purchase, mining, milling or marketing plans are formulated.


Missoula
Helena
Deer Lodge
Anaconda
Butte
Hamilton
Bozeman
Salmon
Dillon
Idaho Falls
Blackfoot
St. Anthony
Rexburg
MONT.
IDA
WYO
For Continuation of Routes See Reverse Side.
To Gooding
To Jerome
To Shoshone
To American Falls To Pocatello
To Montpelier

OFFICIAL FILE COPY
DMEA
RECEIVED JUN 9 1958

DATE	INITIALS	CODE


Logan
Preston
Montpelier
Evanston
Kemmerer
Green River
Rock Springs
Riverton
Lander
Provo
Heber
Price
Vernal
Grand Jct.
Rawlins
Rifle
Craig
Meeker
Dragerton
Helper
Roosevelt
Duchesne
Manila
Dutch John
Green River
Moab
Monticello
Blanding
Bluff
Mexican Hat
Kanab
Page
Tuba City
Cedar City
Beaver
Fillmore
Nephi
Richfield
Salina
Manti
Ephraim
Gunnison
Montrose
Ouray
Durango
Cortez
Dolores
Rangely
Dinosaur
Jackson
Pinedale
Big Piney
Kemmerer
Lyman
Mountain Home
Bonneville
Shoshoni
Thermopolis
Worland
Cody
Powell
Lovell
Basin
Greybull
Meeteetse
Ten Sleep
Buffalo
Kaycee
Douglas
Glenrock
Casper
Mills
Bridger
Cheyenne
Wheatland
Torrington
Lusk
Newcastle
Sundance
Hot Springs
Edgemont
Chadron
Alliance
Scottsbluff
Gering
Bridgeport
Kimball
Sidney
Ogallala
Lexington
Gothenburg
North Platte
Cozad
Ogallala
Imperial
Chase
Wauneta
Grant
Ulysses
Elkhart
Tribune
Leoti
Scott City
Leoti
Garden City
Lakin
Deerfield
Syracuse
Tribune
Ulysses
Elkhart
Stevens
Sublette
Lincoln
Uinta
Sweetwater
Carbon
Albany
Laramie
Converse
Natrona
Fremont
Hot Springs
Washakie
Big Horn
Park
Sheridan
Johnson
Crook
Weston
Campbell
Niobrara
Goshen
Platte
Laramie
Carbon
Sweetwater
Uinta
Lincoln
Sublette



ORE RESERVES AND GEOLOGY OF THE WELLBORN THORIUM PROPERTIES
BEAVERHEAD COUNTY, MONTANA

I N T R O D U C T I O N

Purpose and Scope: At the request of Mr. C. Andrade, III, Tower Petroleum Building, Dallas, Texas, the writer spent April 16, and 17, 1957, on the Wellborn Thorium Property for the purpose of examining and evaluating the deposits.

As deep snow (3-4') covered the surface, little could be seen of the surface and regional ge logy. Snow had been removed from access roads, adit portals and a few open cuts.

Mine records and maps were examined carefully. The report of Mr. Leonard D. Jarrard, Minerals Consultant, Butte, Montana, was an especially valuable aid. Mr. Jarrard enjoys a wide reputation as a sound engineer and much of the Atomic Energy Commission's work at the Wellborn property was done under his direction previous to his leaving the commission.

Location and Accessibility: The property is located just east of the continental divide and the Idaho-Montana border in west central Beaverhead County, Montana (secs. 29, 32 and 33, T.10S., R.15W.). The claims lie 35 miles by road east of Armstead, Montana and 80 airline miles southwest of Butte, Montana (see highway map, next page)

The property may be reached from Butte via U.S. Highway 91, south to Armstead, hence 35 miles over county and mine roads in a general westward direction to the mine. An Union Pacific railroad branch line connects Armstead with Butte, Montana, and Salt Lake City, Utah.

A main line electric power transmission installation passes within 2-3 miles of the property.

Property and Development: The Wellborn thorium properties consist of 33 unpatented lode mining claims. The claims appear to be in good order with assessment work completed for the 1956-57 period. Proof of labor should be filed in Dillon, Montana, county seat of Beaverhead County, if it has not been.

A small camp, made up of several bunk houses, a cook house and dinning hall, and an office building is located along the South Fork of Frying Pan Creek, the main drainage of the area, about one and one half miles from the mine workings.

Exploration work on the claims is extensive. The outcrops have been thoroughly trenched; a 52' shaft has been sunk near the southeast end of the Last Chance-Shady Tree vein; a cross-cut has been driven to intersect the ore at approximately 300 feet vertically below the highest outcrop point. The cross-cut is located near the northwest end of the vein (see map in envelope below). A second cross-cut, planned to intersect the ore structure 180 feet below the first cross-cut has been started and is in about 110 feet of the necessary 1,100 feet.

G E O L O G Y

General Statement: Because of snow conditions very little surface geology could be done during this visit. The writer is familiar with the regional geology of the area.

The property lies within a group of pre-Cambrian rocks that are in contact with the Idaho batholith, a vast igneous intrusive of late Cretaceous age that lies to the west.

The mineralization is associated with structural deformation of the pre-Cambrian, Beltian rocks, that occurred during Laramide times.

Rocks: The host rocks of the ore bodies are metamorphosed sandstones or quartzites. The original sandstone was probably somewhat argillaceous and the resutling metamorphic rock is a dense, brittle, fine-grained, dunn-colored rock.

Structure: The mineralization is associated with northwest-southeast trending fracture and shear zones. The pre-Cambrian quartzite beds are complexly folded and contorted. In general, the beds strike approximately east-west in the vicinity of the Last Chance-Shady Tree ore body, and the fracture zone controlling the ore deposition strikes N. 65-75° W. and dips 45-60° southwest. Other ore bearing structures on the property appear to parallel the Last Chance-Shady Tree structure.

ORE DEPOSITS

Mineralogy: The quartz-hematite-thorium veins are typical of fracture zone fillings. Quartz with considerable iron stain and some specular hematite makes up the greater part of the vein filling material. Thorium minerals occur occassionally as isolated grains in the quartz, but normally they fill the minute fracture systems that make up the structure.

Ore Minerals

Thorite $ThSiO_4$, thorium silicate
Hydrothorite, hydrous thorium silicate
Monazite, rare earth thorium phosphate
Allanite, complex silicate with Th and Y.

Gangue Minerals

Quartz
Hematite
Pyrite
Barite

Thorite appears to be the chief ore mineral. Monazite and allanite are rare and hydrothorite appears to be intimately associated with the iron oxides.

Europium has been reported from this property; a composite sample from the Last Chance-Shady Tree ore body has been sent out for analysis. Assay returns on these samples will not be back for another 2-3 weeks.

Ore Bodies: According to Jarrard's report, there are two more-or-less parallel ore structures on the property, known as the Last Chance-Shady Tree and the Shear Zone ore bodies. The writer's studies were limited to the former because of snow conditions.

The Last Chance-Shady Tree ore body is a strong, apparently continuously mineralized fracture zone that strikes N. 65-75° W. and dips 45-60° SW (See map in envelope, next page).

Exploration work has opened the vein for 2,000 feet along the strike and over a vertical range of 300 feet. The vein varies in thickness from 14 feet to over 30 feet and averages about 22 feet.

Thorium mineralization within the walls is entirely across the structure. There is a higher grade band along the footwall and also near the hanging wall of the structure.

Tenor (grade) of Ore: Using only the samples the writer cut underground, the ore averages 0.685 percent ThO_2 (thoria) (see sample and geology maps, below). The assay values are radiometric, checked against a thorium standard.

Jarrard's report gives a somewhat higher average and is probably more nearly the true grade of the deposit as he had hundreds of chemical and radiometric assay returns from which to make his average.

ORE RESERVES

Since the writer could examine only the Last Chance-Shady Tree ore body, reserves are shown for that structure only. However, Jarrard's report gives the size and grade of other ore bodies.

SHAFT

UNDERGROUND GEOLOGY AND SAMPLE MAP
LAST CHANCE - SHADY TREE ORE BODY
WELLBORN THORIUM PROPERTIES
Beaverhead County, Montana
Scale 1" = 5'



Sample No.	*ThO_2	Width
10	0.652	5'
11	0.621	5'
12	0.628	4'
10-12	0.621	14'

Fault
Quartz
Mineralization

wagner and oberbillig 4/16/57



CROSS CUT
UNDERGROUND GEOLOGY AND SAMPLE MAP
LAST CHANCE - SHADY TREE ORE BODY
WELLBORN THORIUM PROPERTIES
Beaverhead County, Montana
Scale 1" = 20'

Sample No.	*ThO_2	Width
2	0.887	6'
3	0.655	4'
4	0.430	10'
5	0.468	6'
6	0.556	8'
7	1.316	13'
8	0.409	5'
9	0.441	3
*radiometric		
2-6	0.574	34'
7-9	0.975	21'
2-9	0.727	22' (True vein width.

Fault
Quartz
Minerallization
Fracture pattern

wagner and oberbillig 4/16/57.

OFFICIAL FILE COPY
DMEA
RECEIVED JUN 9 1958

DATE	[illegible]	

The writer thinks highly of Jarrard's work and was able to check part of it from available records. An open road cut on the Shear Zone ore body gave an extremely high radioactive anomaly. From the geology of the Last Chance-Shady Tree ore body and the information in Jarrard's report, the figures below are considered to be a minimum.

Using a Strike length of 2,000 feet, a mining width of 18' feet and a down dip distance of 300 feet, the reserves for the Last Chance-Shady Tree ore body would be as follows:

$$\frac{2{,}000' \times 18' \times 300'}{15 \text{ cu.ft./ton}} = 720{,}000 \text{ tons}$$

At a grade of 0.685 percent thoria or 13.7 pounds per ton, these reserves would contain 9,864,000 pounds of thoria. Or at a value of $41.10 per ton, the inground value would be:

$41.10 X 720,000 tons = $29,592,000.00

The $41.10 value is calculated from recently quoted monazite ore prices based on $60.00 for the contained thoria per unit (1 unit = 20 pounds per ton).

The above inground value does not show mining and milling losses, and, at this time it would be hard to calculate these, as nothing is known concerning the beneficiation of thorite ores from this property.

The probability of increasing the reserves with drilling or cross-cutting at depth is excellent.

B E N E F I C I A T I O N

To the writer's knowledge, no beneficiation tests have been run on the ores. As the present thorium ore market demands a 10 percent thoria content, tests should be conducted to determine the amenability of the ores to gravity concentration.

Panning of the ore from the high grade footwall band in the northwest end of the Last Chance-Shady Tree ore body shows some concentration of values. Like other thorite ores of the writer's experience, it is suspected that at least part of the ore will respond to gravity concentration.

The Colorado School of Mines Research Foundation has had considerable experience in concentrating thorite ores and the writer suggests that samples be sent to:

Mr. Ed Crabtree, Director
Colorado School of Mines Research Foundation
Golden, Colorado.

The Foundation's past experience with such ores will allow them to determine the amenability of these ore in a relatively short time. If gravity concentration methods are not feasable, then the more expensive chemical methods of up-grading will be required. Should chemical methods be necessary; then, serious consideration should be given to placing a complete chemical plant at Armstead, Montana, for utilizing the ores from the Wellborn properties.

M I N I N G A N D M I L L I N G

Because of the shattered character and rather flat attitude of the vein some mining problems will be involved. Considerable timber will be necessary, but an abundant supply is on the claims.

Mining costs should not exceed $12.00 per ton. If the ore is delivered to the rail head at Armstead, trucking would be about $3.00 per ton; or, in other words, with careful operation, ore can be delivered to the car at the railhead for $15.00 per ton.

If it is necessary to concentrate the ore to produce a marketable ore, the necessary gravity or flotation plant will cost about $3,000.00 per ton of capacity; or, about $300,000.00 for the construction of a 100 ton plant.

13

Milling costs of concentrating the thorium ore should not exceed $5.00 per ton. By putting the plant at the mine and trucking only concentrates to the rail head, the cost would be about $17.00 per ton for mining and milling plus the cost of trucking concentrates to the railroad.

With the price of thorium ores at $60.00 per unit of ThO_2 (1 unit = 20 pounds or 1% of 2,000 pounds), ore at the Wellborn property would be worth $60.00 X 0.685 = $41.10 per ton. Using a combined mining, milling and trucking cost of $20.00 per ton (this may be high), there would be $21.10 per ton for marketing and profit. The $60.00 per unit of ThO_2 price is F.O.B. the plant of the purchaser (probably about $50 to $60 per ton to the eastern seaboard).

In order to make a market for the thorium from this property, it may be necessary to produce thorium salts or the metal. This would require a chemical plant that would cost about $1,500,000.00 for a 500 ton capacity per year.

Detailed information on the cost of producing thorium salts is not available, but would run somewhere around $2.00 to $3.00 per pound.

M A R K E T

Thorium uses in the United States have steadily increased over the past few years, but a ready market for domestic thorium ores is difficult to find. Lindsay Chemical, Chicago, Ill., will apparently buy thorium ores containing 10 percent or more thoria.

High-temperature thorium bearing magnesium alloys are in demand, and a potential market exists in the nuclear energy field. This usage is not clear, but predictions are that thorium will be used as a fertile reactor material because of its ability to yield fissionable U-233 in breeding type reactors.

14

A recent forecast on thorium by an AEC official indicates that full scale thorium usage in reactors will develop in the next 2, 5 or ten years. Apparently the completion and operation of Consolidated Edison's reactor will furnish much needed technology on thorium in the reactor field.

The price of thorium compounds as quoted on page 101, ENGINEERING AND MINING JOURNAL, Vol. 158, No. 2, Feb. 1957, follows:

Compound	% ThO_2	Price/lb. 100lb.lots.
Carbonate	80-85	$7.25-8.80*
Chloride	50	7.00
Fluoride	80	6.50
Nitrate	46	3.00
Oxide	97-99	8.25-9.35

*variable on rare earth content

Also according to the same source, Consolidated Edison Company purchased from the AEC in 1956, 27,500 pounds of thorium metal for $537,000.00 (about $19.53 per pound).

The outlook for thorium is good in high-temperature magnesium alloys, but much information is needed on thorium's role in nuclear energy.

C O N C L U S I O N S

The strength and persistence of the Last Chance-Shady Tree ore body is sufficient to indicate that the reserves calculated for the property are conservative.

The fact that the thorium market is limited points to the necessity of ore beneficitation tests in order to evaluate properly and to plan the future operation of the property.

Europium has been reported on the property, but assay returns are not back to confirm this; at any rate, the europium market is much less assured than the thorium market.

QUALIFICATIONS

Education:

Berea College, Berea, Ky., B.S. Geology, 1936.
Idaho School of Mines, Moscow, Idaho, M.S. Geology, 1937.
The Johns Hopkins Univ., Ph. D. Geology, 1947.

Experience:

United States Geological Survey, 2½ years.
Anaconda Copper Mining Company, Butte, Mont., 2 years.
University of Idaho, teaching, 1942-1945
Idaho Bureau of Mines and Geology, geologist 1942-1947.
Colorado School of Mines, teaching, 1947-1953.
Colorado School of Mines Research Foundation, Research geologist, 1948-1953.
Geological Consultant, Market Research Industrial Chemicals Mallinckrodt Chemical Works, 1953 to present.
Independent Consulting Geologist. 1953 to present. Serving the Mining, Chemical and Construction Industries.
Consulting Geologist, Arrowhead Urnaium, 1951-1953, and to Arrowhead successor Trace Elements Corporation, 1953'till November 1956.
Companies served are some of the major chemical companies, leading mining companies and several large contractors.

Registered Professional Geological Engineer, State of Nevada, No. 1029.

Warren R. Wagner

Warren R. Wagner

LAST CHANCE-SHADY TREE ORE BODY

SURFACE OUTCROP, CUTS AND PROFILE
AFTER COMPANY MAPS



W.R.W. 4/20/57