

Assays by U. S. Bureau of Mines

NO. 3 TUNNEL

NO. 1 TUNNEL

Samp	water soluble				insoluble			
	Ni	Cu	Co	Fe	Ni	Cu	Co	Fe
WSN-60	1.71	1.10	0.10	0.10	1.04	1.25	0.05	10.5
WSN-59	0.63	0.64	0.06	0.02	0.37	0.51	0.01	14.58

NOTE: All samples 6 feet in length

NOTE: Sample 59 4 feet in length
Sample 60 5 feet in length

Samp	water soluble				insoluble			
	Ni	Cu	Co	Fe	Ni	Cu	Co	Fe
WSN-58	0.03	1.02	0.01	< 0.01	0.50	0.17	0.04	10.8
WSN-57	0.52	0.02	0.05	< 0.01	0.36	0.21	0.02	8.0
WSN-56	0.39	0.12	0.06	0.07	0.08	0.59	0.01	20.28
WSN-55	0.58	< 0.02	0.05	< 0.01	0.32	0.35	0.01	8.0
WSN-54	0.69	< 0.02	0.06	3.25	1.89	0.63	0.05	17.5
WSN-53	0.03	< 0.02	< 0.01	< 0.01	0.75	0.21	0.05	9.8

ASSAY MAP

WINESAP NICKEL PROSPECT

CHELAN COUNTY, WASHINGTON

Figure 1